Page 1 of 2



Nippon Sheet Glass Co., Ltd.



Properties

- C-glass platelet of about 5µm thick and 10~4,000µm wide
- Extends life of protective coating : dispersed through the coating, prevents the ingress of water vapor and chemical solutions
- Prevents cracking and peeling : provides a thermal stabilization layer in the protective • coating
- Improves wear resistance : increases hardness of epoxy and polyester resin coatings •
- Improves chemical resistance: Borosilicate C-glass makes good resistance to chemical attacks, compared to other types of glass

Microglas® Glass Flake is ideal for use in vinyl ester, epoxy, acrylic paints and acrylic coatings as a barrier against corrosive attack by chemicals and moisture.

Refs	Glass	Specific gravity	Thickness (µm)	Particle size distribution (in µm)					Loss of	Surface	Bulk
				>1700	1700- 300	300- 150	150- 45	<45	ignition	treatment agent	density (g/cc)
RCF- 600	C	2.5	5+/-2	0	>8	>80 ·		20	-	-	0.20
RCF- 160	C	2.5	5+/-2	0	<10	>65		<25	-	-	0.40
RCF- 015	C	2.5	5+/-2	0	<12			>88	-	-	0.75
RCF- 160A	C	2.5	5+/-2	0	<10	>6	55	<25	0.15+/-0.10	Amino silane	0.40
RCF- 160N	C	2.5	5+/-2	0	<10	>6	55	<25	0.15+/-0.10	Acryl silane	0.40

Specifications

Microglas® Glass flake is available in a range of surface treatments to suit different resins: N (Acryl silane) for vinyl ester / A (Amino silane) for Epoxy



Packaging

Microglas® Glass Flake is supplied in moisture proof paper bags, each containing 20kg net weight. For bulk shipments, the bags of glass flake are palletised and further protected by cardboard and polyethylene wrapping:

- **RCF-600** 14 x 20 kg bags = 280 kg total net weight per pallet
- **RCF-160** 28 x 20 kg bags = 560 kg total net weight per pallet
- **RCF-015** 48 x 20 kg bags = 960 kg total net weight per pallet

FRP Services reserves the right to change the information given herein without prior notice. We believe this information to be reliable, but do not guarantee its applicability to the user's process or assume liability for occurrence arising out of its use. The user, by accepting products described herein agrees to be responsible for thoroughly testing any application before committing to production.



FRP SERVICES & COMPANY 1-15-9 Awaza, Nishi-ku, Osaka 550-0011, Japan TEL:+81-6-6535-1933 FAX:+81-6-6535-1675 www.frpservices.com