

SINGLE YARN

TAIWAN GLASS IND., CORP.



SPECIFICATIONS

Style		Tex (g/1000m)	Solids (%)	Moisture (%)	TPC (turns)		Strength (gf/tex)	Broken Filament
EC9 136	ECG 37	134.00±3.00	1.15±0.20	<0.20	0.70±0.20	28±8	mini 48	maxi 10
EC9 75	ECG 67	72.00±1.75	1.10±0.20	<0.20	0.70±0.20	28±8	mini 48	maxi 10
EC9 68	ECG 75	68.30±1.75	1.10±0.20	<0.20	0.70±0.20	28±8	mini 48	maxi 5
EC9 34	ECG 150	33.10±1.00	1.20±0.20	<0.20	0.70±0.20	28±8	mini 48	maxi 5
EC7 45	ECE 110	45.00±1.25	1.25±0.20	<0.20	0.70±0.20	28±8	mini 50	maxi 5
EC7 22	ECE 225	22.30±0.75	1.55±0.30	<0.20	1.00±0.20	40±8	mini 50	maxi 5
EC6 34	ECDE 150	33.10±1.00	1.30±0.20	<0.20	1.00±0.20	40±8	mini 55	maxi 5
EC6 16	ECDE 300	16.60±0.50	1.80±0.30	<0.20	1.00±0.20	40±8	mini 55	maxi 5
EC5 11	ECD 450	11.10±0.50	1.85±0.30	<0.20	1.00±0.20	40±8	mini 60	maxi 5
EC5 5.5	ECD 900	5.10±0.50	1.85±0.30	<0.20	1.00±0.20	40±8	mini 60	maxi 5

PACKAGING

Style		Bobbin type	bobbin weight (g)	T1 / 80% (kg)	T2 / 20% (kg)	Loading quantity (bobbins)	
						20'	40'
EC9 136	ECG 37	8570	546	8.75	mini 4.00	1 120	2 240
EC9 75	ECG 67	8570	546	7,37	mini 4.00	1 120	2 240
EC9 68	ECG 75	8570	546	8.75	mini 5.00	1 120	2 240
EC9 34	ECG 150	8540	292	2.65	mini 2.00	2 400	4 800
EC7 45	ECE 110	8540	292	3,50	mini 2.00	2 400	4 800

STORAGE

TGI's yarn should be stored dry in its original packaging.
Storage temperature : max. 35 °C – Relative moisture : < 70 %

FRP Services Europe reserves the right to change the information given herein without prior notice. We believe this information to be reliable, but do not guarantee its applicability to the user's process or assume liability for occurrence arising out of its use. The user, by accepting products described herein agrees to responsible for thoroughly testing any application before committing to production.



FRP SERVICES EUROPE

BP 204 - 13796 Aix-en-Provence Cédex 3 - FRANCE

Tel : +33 (0)442 97 59 10 / Fax : +33 (0)442 97 59 20

e-mail : info@frpeufr.com